



Original article

## ENERGY VALUE AND RELATED PROPERTIES OF CHRIST'S THORN (*Ziziphus spina-Christi*)(L.) Desf.

Wakili, A<sup>1</sup>., Yusuf, A<sup>2</sup>. And Gawaisa, S<sup>3</sup>.

<sup>1</sup>Forestry Department, School of Agricultural Technology, Federal Polytechnic, Bauchi-Nigeria

<sup>2</sup>Bauchi State Agricultural Development Programme, Dass Road Bauchi- Bauchi State

<sup>3</sup>Department of Forestry and Wildlife Management, School of Agriculture and Agricultural Technology, Modibbo Adama University of Technology Yola, Adamawa State-Nigeria

Submitted: October; Accepted: December; Published: December, 2018

### ABSTRACT

The stems and roots of phanerophytes are made of a porous and fibrous structural tissue that are strong in tension and embedded in matrix of lignin that resist compression. Wood is fibrous material used for biofuel or timber in addition to being used as pulp for making paper. A fresh wood sample of *Ziziphus spina-Christi* (Christ's thorn) was taken from Buskuri open savanna woodland and tested for moisture content, calorific value, combustion rate and its coppicing ability measured. The study showed that the moisture content at the time of energy determination was found to be 5.62 percent and the calorific value of 15.33 Mj/Kg was recorded. The results also revealed that in eight minutes, the temperature of the wood sample reached 450°C and temperature above 100°C was retained for a period of 22minutes. The species was found to coppice at the rate of 155cm per annum. An urgent need to stop cutting *Ziziphus spina-Christi* for fuel wood and the need for further research on the wood properties of the same species for enhanced diversification of utilization were recommended.

**Key words:** Calorific value-Coppice-Combustion rate-Temperature-Moisture

Corresponding Author: [adamuwakili1@gmail.com](mailto:adamuwakili1@gmail.com) +2348029409211

### INTRODUCTION

*Ziziphus spina-Christi* (L.)Desf. is a tropical drought resistant tree with a thick

fissures bark belonging to family Rhamnaceae. It grows to the height of between 25m-35m when fully mature, it is an ever green with a spiny branches which

spread irregularly or pendulous forming round foliage. The trees bear heavy yields- as many as 25000 fruits annually on a mature tree in good condition. The fruit is oval to round in shape and edible to both human and animals. *Ziziphus spina-Christi* (L.)Desf. has wide ecological amplitude within African continent and one of the oldest plant upon which mankind depends for valuable resources [1].

Forest in the tropical developing nations are extensively used for grazing, fuel wood collection, cutting for medicinal purposes and other numerous subsistence needs by local people even inside protected areas that have been prioritized for biodiversity conservation [2]. The heavy dependence on wood for fuel and timber products has contributed to the accelerated forest and woodland degradation. This is particularly serious where population is dense and with little or substitute of biofuel as a result of lean financial earnings.

Fuel wood is the dominant energy form throughout Africa and the rest of developing world ([3]; [4]). The importance of fuel wood in economic development cannot be overemphasized. Fuel wood collection is a common and widely practiced economic activity of the rural dwellers and this was necessitated by the ever increasing demand for fuel wood as a formidable source of energy for household cooking, barbecuing, bakery and blacksmithing industries, fish smoking and oil palm production [5].

Forest provides the bulk of domestic energy for cooking and space heating among the rural communities in Nigeria [6]. This is due to its availability, accessibility, affordability and simplicity in utilization. Other forms of energy of fossil origin are beyond economic

capability of the majority of people living in rural areas. In addition, the supply of such energy is limited and erratic.

Presently due to increased loss of floral biodiversity, fuel wood collection is indiscriminate as a result; species of low energy value but of higher pharmaceutical, constructive and conservative values and other numerous socio-economic attributes are being carelessly removed. This leads to the loss of species of high quality timber and pharmaceutical potentials, and its attendant deforestation that leads to severe environmental degradation. To stop this ecologically ill practice, it is of paramount importance to investigate the energy related attributes of commonly used woody species in order to show case same to the teeming fuel wood users, government and non-governmental organizations within developing nations, so that a choice can be made in terms of utilization and woodlot establishment and management [1]Energy sources need to be managed for enhanced sustained yield that will guarantee benefits for present and future generation.

The aims of this study were to determine Calorific value, Combustion rate and Coppicing ability of *Ziziphus spina-Christi* with a view to either encourage its usage for fuel wood plantation schemes in the tropics or discourage its utility for energy generation because of its poor energy related properties.

## **MATERIALSANDMETHODS**

### **Collection of wood sample**

A fresh wood sample of Christ's thorn was obtained from Buskuri open woodland forest in Bauchi State, Nigeria (9<sup>0</sup>30<sup>1</sup> and 12<sup>0</sup> 30<sup>1</sup> North of the equator and longitude 8<sup>0</sup>50<sup>1</sup> and 11<sup>0</sup> east of the Green witch

meridian). This forest is denuded woodland as a result of anthropogenic activities spear headed by fuel wood collection. The collection was made in the dry season. The collected sample was tested for moisture, calorific value, combustion rate and its regeneration effort measured.

#### **Determination of Moisture content**

The apparatus used for this test were an electric oven (DHD 1901), digital weighing balance, wet and dry bulb thermometers. The wood sample was introduced in to an oven maintained at 105°C for one to four hours until uniform weight was attained and the moisture was determined using an equation below in accordance with ASTM-D143-82.

$$MC = \frac{A-B}{B} * 100$$

Where MC = Moisture content, A = Original mass of sample, and B = Oven dry mass of sample

#### **Determination of Calorific Value**

To determine the energy value of the wood sample, a bomb calorimeter (LECO-AC-350) and an electric balance were used in accordance with ASTM-D143-82. The analysis was conducted at National Metallurgical Centre Jos, Plateau State-Nigeria.

#### **Determination of Combustion Rate**

The apparatus used were Pyrometer, Thermocouple and Crucible. The test was conducted in a form of open fire under indoor condition. After ignition, the wood sample was allowed to flame until completely burnt in to ash. 30g of the wood sample was put in to crucible. The sample was ignited using matches and a little kerosene. The temperature of the

burning sample was taken at an interval of two minutes until it completely get burnt. This test was conducted at the thermodynamics laboratory, Abubakar Tafawa Balewa University, Bauchi-Nigeria.

#### **Determination of Regeneration Ability of the Species**

The natural regeneration ability of the species was measured by observing its stump that gives out coppice shoot under natural condition. An annual average height and number of successful coppice shoot were measured. An average height of the species was obtained by summing of all yearold re-growth of five stools of the species and divided by number of the species (stools). The number of the coppice shoot that graduated in to tree size were considered as successful coppice shoot.

## **RESULTS AND DISCUSSION**

### **Moisture content**

The moisture content of *Ziziphus spina-Christi* at the point of energy determination (5.62%) was found to be below equilibrium moisture content of 15% [7]. This is because when the fresh sample of the wood was collected, it was splitted there by exposing much of the wood surface to the drying wind and sun. Wood begins to dry out as soon as it is cut and progress through several stages. In the first stage of drying, free water is lost until fibre saturation point is reached. Drying beyond this point to equilibrium moisture content takes progressively longer, since it involves the removal of bound water. The moisture content at this levels and the rate of drying vary depending on humidity and temperature [8]. Since even at 25% moisture content, 80% of the content energy will be available for utility [9], drying wood sample to as low as 5.62%

will necessitate the release of all the quantum of energy of the wood sample.

### Calorific Value

The results of calorific value determination indicate that *Ziziphus spina-Christi* wood sample contains 15.33Mj/Kg at the time of bomb calorimetric analysis as a result of low moisture of the sample. Moisture content of wood is one of the major determinants of wood's energy for utilization. The energy value obtained is higher than that of *Anogeissus leiocarpus* (23.945Kj/Kg) and *Prosopis africana* (20.925Kj/Kg) at 10.75% and 9.82% moisture content respectfully as reported by [10]. The variation may be as a result of differences in moisture content because moisture affects the production of usable energy when wood is burnt [7].

However, the energy value obtained in this study is lower than the energy value of some fuel wood tree species reported by [1]; [11]. The former reported the energy value of 16.554Mj/Kg for *Anogeissus leiocarpus* and the later reported energy value of 17.934 Mj/Kg for *Prosopis africana*. The energy value obtained from this study will not provide the needed energy for small and medium enterprises, and homes which are dependent on wood as a source of energy. The energy value of *Ziziphus spina-Christi* (15.33Mj/Kg) indicates that much quantity is needed to carry out a heating or cooking exercise and by extension, many trees of the same species must be cut in order to have the required quantum of energy. This will increase the rate of deforestation and its attendant environmental degradation. The valuable money and time needed to

address other important issues at the family and community levels are being wasted in acquiring less energy value wood.

### Combustion Rate Test

The combustion rate test of *Ziziphus spina-Christi* indicated that in eight minutes the highest temperature of 450°C was reached and which in just two minutes dropped to 400°C and progresses to 90°C in sixteen minutes there after (Table 1). Temperature above boiling point was maintained for a period of 24 minutes and there after the heat drastically dropped. The combustion rate test of *Acacia hebecladoeids* showed that in ten minutes, a peak temperature of 335°C was obtained in 26minutes and dropped to 110°C in 28 minutes, and maintained temperature above 100°C for 25minutes [8]. Comparatively also, [1] reported that *Anogeissus leiocarpus* attained a temperature of 320°C in ten minutes. *Ziziphus spina-Christi* attains the highest temperature (450°C) among these tree species but this temperature drops immediately indicating that it will not be suitable for heating operations requiring a sustained heat for longer period of time. Since many contributors ([12]; [13]; [14]) have reported areas where *Ziziphus spina-Christi* plays an important role in solving a variety of socio-economic problems: suitability of its wood for agricultural hand tool handles, forage tree, apicultural tree, fruits used for votive offerings, medicinal attributes and conservative values among others, the attention be therefore tailored towards provision of these vital goods and services rather than cutting this species for fuel wood.

**Table 1. Combustion rate test of *Ziziphus spina-christi* (L.) Desf.**

Time(minutes)	Temperature (°C)
0	30
2	98
4	210
6	410
8	450
10	400
12	360
14	310
16	282
18	270
20	220
22	200
24	170
26	130
28	90

### Coppicing Ability of *Ziziphus spina-Christi*

The coppicing ability of *Ziziphus spina-Christi* was observed in Buskuri open forest by noticing the presence and measuring the height of coppice re-growth from the stool of the same species. It was observed that the stool profusely coppice and the coppice shoot can grow at the rate of more than 155cm per annum. This clearly indicates that this species can be used in the establishment of other forms of plantations rather than woodlot. The fast growing nature of this species makes it a good candidate for such a project meant to produce small sizable wood within the shortest period of time. Its double root system can adequately support its coppice shoot. *Acacia hebecladoeids* was reported to coppice at the rate of 135cm per annum, [8].

### CONCLUSION

*Ziziphus spina-Christi* has little energy value compared to many fuel wood tree species even though the temperature of the available calories can be maintained for a considerable period of time. This indicated that this species is not suitable for fuel wood but since it was reported that the species plays a vital role in the provision of wood for tool handles, construction, and pharmaceuticals, the species can be managed for these reasons rather than fuel wood.

### RECOMMENDATIONS

1. That there is an urgent need to stop cutting *Ziziphus spina-*

- Christi* for fuel wood because of its low energy content.
2. That the species (*Ziziphus spina-Christi*) will be good for timber plantation because of its strong and durable wood.
  3. That as an incentive, plantation inputs be made available to all intending plantation developers free of charge by both government and non-governmental organizations.
  4. That there is the need for further research on wood properties of *Ziziphus spina-Christi* for enhanced diversification of utility.
  5. As a forage species, its proximate analysis will help to unveil its nutritive value and hence categorization for animal production.

## REFERENCES

1. Wakili, A., Gani, A.M. and Abdul, S.D. (2009). Calorific value and related properties of *Anogeissus leiocarpus* as one of the most common fuel wood species in Bauchi metropolis. *Journal of League of Researchers in Nigeria*, 10(1): 47-49.
2. Kothari, A., Pande, P., Singh, S. and Variava, D. (1989). Management of National Park and Sanctuaries in India: a status report, Delhi India. Indian Institute of Administration.
3. Pandey, D. (2002). Fuel wood studies in India: Myth and reality, Bogor CIFOR
4. Hall, O.O. (1991). Biomass Energy. *Energy Policy*, 19: 3-11.
5. Tella, I.O., Akpan, M., Ijomah, J.U. and Wakili, A. (2005). Fuel wood consumption pattern of the rural communities of Adamawa State, Nigeria. *Journal of Environmental Sciences*, 9(2):89-96.
6. Akpan, M., Wakili, A. and Akosim, C. (2005). Fuel wood Consumption Pattern In Bauchi State: A guide for Energy Planers in Nigeria. *International Journal of Agricultural Sciences, Sciences, Environment and Technology*, 5(11): 70-75.
7. Zobel, B. J. and Van Bujitenem, J.P. (1989). Wood variation, its causes and control. *Springer Verlag*, Berlin 363pp.
8. Wakili, A., Garba, A., Mato, A. and Kyauta, E.E. (2012). Calorific value and related properties of *Acacia hebecladoies* as one of the common fuel wood tree species in Tafawa Balewa metropolis, Tafawa Balewa LGA Bauchi State, Nigeria. *JOLORN*, 13(2):18-24.
9. Reyes, G., Brown, S. Chapman, J. and Lugo, A.E. (1992). Wood Densities of Tropical Tree species General Technical Report 50/88 United States Department of Agriculture, Forest Services Southern Forest Experimental station, New Orleans.
10. Onuarah, E.O. (1999). The energy value and related characteristics of twenty-two of the Most commonly used fuel wood species of Makurdi

- L.G.A. and Environs. *Nigerian Journal of Renewable Energy*, 7(1 and 2): 87-90.
11. Wakili, A. and Abdullahi, M.B. (2010). Identification of Fuel wood Tree species in Bauchi State *Agriculture, Bussiness and Technology Journal*, 8(2):51-58.
12. Chapagain, B.P. (2006). Characterization of Desert Date (*Balanites aegyptiaca*) Saponins and their Biological activities. Unpublished Ph.D Thesis, Ben-Gurion University of the Negev: 1-5.
13. Usama, A. A. R. (2007). Photosynthetic and Leaf Anatomical characteristics of the Drought-Resistance *Balanites aegyptiaca* seedlings. *American-Eurasian J. Agric and Environ. Sci.* 2(6):680-688.
14. Abdullahi, M.B., Tahir, F. Shuaibu, A. and Wakili, A. (2010). Common medicinal Plant species of Maladumba area, Misau, Bauchi State- Nigeria. *International Journal of Applied Biological Research*, 2(2):102-109.